

# Environmental Product Declaration



**Ytong<sup>®</sup> Autoclaved Aerated Concrete** 

Xella Baustoffe GmbH

Declaration number EPD-XEL-2009112-E

Institut Bauen und Umwelt e.V. (Institute Construction and Environment e.V.) www.bau-umwelt.com



		Summary
		Environmental Product-Declaration
Institut Bauen und Umwelt e (Institute Construction and Environmer www.bau-umwelt.com	e.V. ht e.V.)	Execution Body
Xella Baustoffe GmbH Franz-Haniel-Platz 6-8 D – 47119 Duisburg	<b>xella</b>	Declaration Holder
EPD-XEL-2009112-E		Declaration Number
Ytong <sup>®</sup> Autoclaved Aerated Concrete		Declared building
This declaration is an Environmental Product Declar environmental performance of the above-mentioned development of environmental and health compatible All relevant environmental data is disclosed in this va	ation according to ISO 14025 and describes the building products. It is intended to promote the e construction. alidated declaration.	products
This EPD is based on the product category rules 'PC	CR Autoclaved Aerated Concrete: 11-2004'	
This validated declaration authorises the holder to be the above-mentioned products for three years from t for the information and evidence on which the declar	ear the official stamp of the IBU. It only applies to he date of issue. The declaration holder is liable ation is based.	Validity
<ul> <li>This declaration is complete and contains in detail:</li> <li>Product definition and physical data</li> <li>Information about raw materials and origin</li> <li>Specifications on manufacturing the product</li> <li>References for product processing</li> <li>Information on product in use, singular effects</li> <li>LCA results</li> <li>Evidence and verifications</li> </ul>	and end of life	Content of the Declaration
February 16 <sup>th</sup> , 2009		Date of Issue
Whennames		Signatures
Prof. DrIng. Horst J. Bossenmayer (President of the Institut Bauen und Umwelt e.V.)		
This declaration and the rules it is based on, have be (SVA) according to ISO 14025.	een verified by the Independent Advisory Board	Verification of the Declaration
h han	Escale	Signatures
Prof. DrIng. Hans-Wolf Reinhardt (Chairman of the SVA)	Dr. Eva Schmincke (Verifier appointed by the SVA)	



### Summary

#### Environmental Product-Declaration

The products mentioned are non-reinforced building blocks in various formats made of autoclaved aerated concrete. AAC belongs to the porous steam-cured light-weight concrete group.				Product Description
Non-reinforced building blocks for brick-la intended, no direct contact with groundwa and there is no direct contact with soil.	aid, monolithic, load-b ater is possible, becau	earing and non-lo use aerated concre	ad-bearing walls. As ete is always coated	Range of Application
The Lifecycle Assessment (LCA) was carried out according to DIN ISO 14040 et sqq. Specific data by Xella from 2004 was used as a database, along with average data for the raw materials used, such as cement, quick lime, anhydrite or aluminium powder and paste. The LCA was carried out for the manufacturing phase of aerated concrete for gross density categories 400 kg/m <sup>3</sup> (P2 0.40) and 500 kg/m <sup>3</sup> (P4 0.50) taking into account all the background information, like raw material exploitation and transports ("cradle to gate"). Comparison with other products is only permissible in the context of comparable use within the building.				Scope of the LCA
Ytong <sup>®</sup> - Autoclaved	Aerated Concrete P	2 0,40 and P4 0,5	0	Results of the LCA
Indicator	Unit per m <sup>3</sup>	P2 0.40	P4 0.50	
Primary energy, non-renewable	[MJ]	1427	1683	
Primary energy, renewable	[MJ]	74	76	
Global Warming Potential (GWP 100)	[kg CO <sub>2</sub> -eqv.]	179	217	
Ozone Depletion Potential (ODP)	[kg R11-eqv.]	10.0 * 10 <sup>-6</sup>	10.9 * 10 <sup>-6</sup>	
Acidification Potential (AP)	[kg SO <sub>2</sub> -eqv.]	0.263	0.285	
Eutrophication Potential (EP)	[kg PO <sub>4</sub> -eqv.]	0.044	0.049	
Photochemical Ozone Creation Potential (POCP)	0.042	_		
Issued by: PE International GmbH, Leinfelden-Echterdingen				
The following evidence and verifications	are also described in	the Environmental	Product Declaration	Evidence and Verifications
Radioactivity	Measurement of radionuclides			
Leaching out properties	According to class 1 from Human Settlem	of the Technical I nents	nstructions on Waste	



Product group:	Autoclaved Aerated Concrete
Declaration holder:	Xella Baustoffe GmbH
Declaration number:	EPD-XEL-2009112-E

#### 0 Product definition

Product definition	The products mentioned of autoclaved aerated co concrete group.	are no oncrete.	n-reinforced building blocks in various formats made AAC belongs to the porous steam-cured light-weight
Range of application	Non-reinforced building blocks for brick-laid, monolithic, load-bearing and non-load- bearing walls. As intended, direct contact with ground water is avoided thanks to the constructional features.		
Product standard/ approval	DIN 4165, DIN 4166, DIN EN 771 part 4; general approval by the building authorities of the German Institute for Structural Engineering (DIBt).		
Quality control	Supervision by the manustandards/general appro 9001.	ufacture wal by b	r and externally according to the above-mentioned ouilding authorities, QM system according to DIN EN
Geometric data	Measurements according the building authorities.	g to DII	V 4165, DIN 4166, DIN 4223 and general approval by
Physical data	Gross density: Pressure resistance: Tensile strength: Bending tensile strength E-Module: Steam-diffusion resistan Equilibrium moisture corr Shrinkage according to	: 750 - 33 ce figur ntent at DIN EN	$\rho = 0.3 - 0.8 \text{ kg/dm}^3$ $\beta = 2.0 - 10.0 \text{ N/mm}^2$ $\beta = 0.24 - 1.2 \text{ N/mm}^2$ $\beta = 0.44 - 2.2 \text{ N/mm}^2$ $250 \text{ N/mm}^2$ e µ according to DIN 4108 T4: 5/10 73.4 °F, 80 % air humidity: < 4 M-% 1680 < 0.2 mm/m
Thermal insulation	Heat conductivity:	accordi	ng to DIN 12664, $\lambda_{\text{R}}$ = 0.09 $-$ 0.18 W/m* K

Table 1: Specific data for various gross density categories

	Ytong <sup>®</sup> - Aerated Autoclaved Concrete							
	Density category	PPV	V 2	PPW 4		PPW 6	Dimension	
	Gross density category value	0.35	0.40	0.50	0.55	0.60	0.65	-
	Average of compressive strength value	≥ 2	2.5		≥ 5.0		≥ 7.5	N/mm²
	Calculation value of heat conductivity $\lambda_R$ according to approval	0.09	0.10	0.12 0.13	0.14	0.16	0.16/ 0.18	W/(mK)
Sound proofing	Sound proofing R' <sub>w,R</sub> :	= 26.1 k	og m' –	8.4 [dB	] accor	rding to	DIN 4109	

**Fire protection** Depending on the formation of the wall, fire resistance categories up to F 180 according to DIN 4102 are attainable.



Product group:	Autoclaved Aerated Concrete
Declaration holder:	Xella Baustoffe GmbH
Declaration number:	EPD-XEL-2009112-E

Issued 05-02-2009

#### 1 Raw materials

Raw materials primary products	Sand Cement Quick lime Anhydride/plaster Aluminium	60 – 70 M-% 15 – 30 M-% 10 – 20 M-% 2 – 5 M-% 0.05 – 0.1 M-%				
	In addition, 50 – 75 M-%	water is used (in relation to the solid substances).				
Auxiliary substances/ additives	Mould oil					
Material explanation	<b>Sand:</b> The used sand is components and traces or significant raw material for	a natural raw material that contains natural minor of minerals, along with the main mineral quartz (SiO <sub>2</sub> ). It is a or the hydrothermal reaction during steam-curing.				
	<b>Cement:</b> Acc. to DIN EN produced using limestone materials are burned and	197-1; cement is used as a bonding agent and is mainly e marl or a mixture of limestone and clay. The natural raw subsequently ground.				
	<b>Quick lime:</b> Acc. to DIN EN 459; quick lime is used as a bonding agent and is produced by burning natural limestone.					
	Anhydride / plaster: Act influence the solidification or is manufactured artific	c. to DIN 1168; the sulphate carrier used is utilized to n period of the AAC and either comes from natural deposits ially.				
	Aluminium: Aluminium p the release of hydrogen of once the expanding proc	bowder or paste is used as a pore-forming agent. It reacts to gas in the alkaline milieu, which forms pores and escapes ess is concluded.				
	Water: The presence of agent. Moreover, water is	water is the basis for the hydraulic reaction of the bonding s necessary to produce a homogenous suspension.				
	<b>Mould oil:</b> Mould oil is the mass from the mould. PA additives to increase viso economical use.	e release agent to separate the autoclaved aerated concrete H is used – free mineral oils with addition of long-chain sosity. This prevents any run-off in the mould and enables				
Raw material extraction and origin	The sand is from sand pi raw materials (apart from from a surrounding area	ts within immediate proximity to the AAC plant. Any other the slight amounts of aluminium powder or paste) come of at most 200 kilometres from the plant.				
Availability of raw materials	Mineral building products mineral raw materials. Th	such s autoclaved aerated concrete mainly consist of nere is no shortage of resources.				

#### 2 Manufacturing the building product

Manufacturing the building product The ground quartz sand is mixed with chalk, cement and AAC recycling material that has been reduced to small pieces, water and aluminium powder or paste, in a mixer, until it becomes a watery suspension. It is then poured into a casting mould. The water extinguishes the chalk if there is any heat development. The aluminium reacts in an alkaline milieu. Thus, gaseous hydrogen is formed which creates pores in the mass and escapes without leaving any residue. The pores usually have a diameter of 0.02 – 0.06 inches and are filled exclusively with air. After setting once, semisolid raw blocks are created, from which the autoclaved aerated concrete building components are then cut with high precision.



Product group:	Autoclaved Aerated Concrete
Declaration holder:	Xella Baustoffe GmbH
Declaration number:	EPD-XEL-2009112-E

Issued 05-02-2009

The formation of the final qualities of the building component occurs during the subsequent steam-curing over 5-12 hours at approximately 374 °F with approximately 12 bar pressure in steam pressure kettles or autoclaves, as they are called. The used substances create calcium silicate hydrate, which corresponds to the naturally occurring mineral tobermorite. The reaction of the material is complete when removed from the autoclave. Therefore, the reaction does not take as long as the hardening of concrete. Once the steaming process is complete, the steam is used for other autoclave cycles. The condensation accumulating is used as process water. Thereby, energy is saved and harm to the environment due to hot exhaust steam and wastewater is avoided. AAC building blocks are then piled onto wooden palettes and shrink-wrapped in polyethylene wrap.

Health protection<br/>(during<br/>production)The body of rules and regulations of the employers' mutual insurance association<br/>applies. No special measures need to be taken for the protection of employees'<br/>health.

**Environmental** The general legal foundations apply. No special measures need to be taken for the protection of the environment. **production** 

#### 3 Working with the building product

Processing recommen- dations	AAC building blocks are worked with manually. Lifting gear is necessary with building components with a mass over 25 kg. Building blocks are cut using band saws or by hand with carbide metal saws, as this only generates coarse dust particles rather than fine dust. High-speed tools, such as abrasive cutting-off machines are inapplicable for working with AAC, as they release fine dust articles.
	The AAC building blocks are cemented to each other or to other standardised building materials using thin-bed mortar according to DIN 1053, part 1; in special cases, normal or light mortar (11 kg mortar / m <sup>3</sup> ) can also be used. The AAC building blocks can be plastered, coated or painted. Alternatively, it is possible to line with small-sized parts or to affix facing shell according to DIN 1053, part 1.
	To assess mortars and coatings, the corresponding IBU-declarations must be taken into account.
Job safety / environmental protection	The body of rules and regulations of the employers' mutual insurance association applies. The thin-bed mortars used when working with autoclaved aerated concrete are mineral mortars and hardly contain any organic substances, apart from methylcellulose.
	No special measures need to be taken for the protection of the environment when working with the building material.
	When selecting any additional auxiliary materials necessary, make sure that the quality does not negatively influence the environmental sustainability of the building products described.
Residual material / packaging	Any packaging, palettes or remaining AAC accumulated on the building site must be collected. The polyethylene shrink-wrap is recyclable. Any PE sheets that have not been soiled (care must be taken that the collection is not mixed).

#### 4 Building product in use

**Constituents** As explained in point 2 "Manufacturing the building product", autoclaved aerated concrete mainly consists of tobermorite, a natural mineral. It also contains not reacted raw components, predominantly coarse quartz, if applicable carbonates. The pores are completely filled with air.



Environmental health effects	AAC does not emit any contaminants such as VOCs. The natural ionising emission of AAC products is extremely low and harmless in terms of health.
Long term durability	AAC does not change once it leaves the autoclaves. When used as intended, it is boundlessly stable.

#### 5 Singular effects

_	
⊢	r۵
	16

No toxic gases or vapours are released in case of a fire. The products referred to fulfil the requirements of building product category A1, "non-flammable" according to DIN 4102.

Water When exposed to water (e.g. floods), AAC has a slight alkaline reaction. However, no substances are washed out which could be harmful to the water.

#### 6 End of life phase

Reuse and downuse	AAC outlasts the service life of the buildings it is used for. This means that when this type of building is dismantled, the materials can be used again with no concerns regarding their durability. The reuse of assembly components made from AAC has been and is still put into practice. Up till now, walled AAC building blocks have hardly ever been reused.
Recycling and downcycling	Unmixed AAC surpluses can be returned to the AAC manufacturers and recycled. This has been done for decades for production residues. This material is either processed to granules or is added to AAC mixture as a substitute for sand.
Disposal	The capacity of AAC to be landfilled according to class 1 of the Technical Instruction Waste From Humans Settlements is guaranteed.

#### 7 Life cycle assessment

#### 7.1 Production of Ytong<sup>®</sup>

Declared unit	The declared unit is 1 m <sup>3</sup> Ytong <sup>®</sup> -AAC non-reinforced from gross density class P2 0.40 (gross density 380 kg/m <sup>3</sup> ) and P4 0.50 (485 kg/m <sup>3</sup> ). Ytong <sup>®</sup> -AAC gross density class 0.40 is the most produced AAC by Xella, with a a percentage of over 40%, followed by gross density class 0.50 at 30%.
System boundaries	The system boundaries selected cover the production of Ytong <sup>®</sup> -AAC from raw material extraction to the finished packaged product at the factory gate (cradle to gate).
Cut-off criteria	All material flows that enter the system and are bigger than 1% of their entire mass or contribute more than 1% to the primary energy consumption, are taken into consideration on the input side.
	All material flows that exit the system and whose environmental impact makes up more than 1% of the total impact in an impact category considered, are covered on the output page.
Transports	All transportation of raw and auxiliary materials used was considered in the assessment.
Period under consideration	The data for the production of the building materials analysed (Ytong <sup>®</sup> -AAC) are based on the year 2004.
Background data	The data base GaBi 4 / GaBi 2003/ was used to calculate the energy generated and the transport. In detail, this covers:

Environmental Product Declaration Ytong<sup>®</sup> - Autoclaved Aerated Concrete

Product group:	Autoclaved Aerated Concrete
Declaration holder:	Xella Baustoffe GmbH
Declaration number:	EPD-XEL-2009112-E

Issued 05-02-2009

Page 8

- The compositions of all used substances (preliminary products)
- Expenditure for production (energy, waste, emissions)
- Preliminary products and energy supply
- Transport and packaging of raw materials and preliminary products

lime

sand

cement

- **Data quality** The data collection for the building materials analysed was carried out in the plants directly. The major part the data for the upstream chain comes from industrial sources which were compiled under consistent boundaries in terms of time and methods. Emphasis was put on obtaining a thorough collection of environmentally relevant material and energy flows. The data can therefore be considered to be of a very high quality. Allocation Allocations (the classification of the environmental pollutants of a process on several products) were carried out according to mass for the by-products.
- ProductionThe process steps taken intoprocessconsideration in the life cycle inventory<br/>analysis are shown in figure 1:
- aluminium 000 water mixing casting creating of pores cutting steamcuring

Figure 1: Flow diagram of the production process of Ytong®-AAC

#### (Source: Ytong®/Xella, modified)

#### 7.2 Description of the balances and analyses

**Life Cycle** Table 2 shows the primary energy consumption (renewable and non-renewable) for the production of 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC for both gross density categories P2 and P4.

 Table 2:
 Primary Energy Consumption for the Production of 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC

Ytong <sup>®</sup> - AAC P2 0.40 and P4 0.50			
Indicator	Unit per m <sup>3</sup>	P2 0.40	P4 0.50
Primary energy, non-renewable	[MJ]	1427.0	1683.3
Primary energy, renewable	[MJ]	74.3	75.6

Closer examination of the required energy (figure 2) for the production of both gross density classes of Ytong<sup>®</sup>-AAC reveals that natural gas is used as the major primary energy source, followed by coal, lignite, crude oil and uranium. The high proportion of natural gas in the primary energy consumption is due to the use of steam for steam-curing.



Product group: // Declaration holder: // Declaration number: //

Autoclaved Aerated Concrete Xella Baustoffe GmbH EPD-XEL-2009112-E Issued 05-02-2009



## Figure 2: Breakdown of the consumption of non-renewable and renewable primary energy of 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC

In addition, approx. 67 MJ/m<sup>3</sup> AAC energy from secondary fuels (used oil, used tyres etc.) are used for P2 0.40 and approx. 63 MJ/m<sup>3</sup> for P4 0.50.

Most of the material resources used are necessary to produce the ingredients: limestone (225 kg/m<sup>3</sup> AAC for P2; 273 kg/m<sup>3</sup> for P4), sand/gravel (233 kg/m<sup>3</sup> AAC for P2; 304 kg/m<sup>3</sup> for P4), plaster / anhydride (21 kg/m<sup>3</sup> AAC for P2; 19.5 kg/m<sup>3</sup> for P4), clay (4.6 kg/m<sup>3</sup> AAC for P2; 4.4 kg/m<sup>3</sup> for P4) and bauxite (2.6 kg/m<sup>3</sup> AAC for P2 and P4).

The analysis of the waste accumulated for the production of 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC in both gross density classes is presented separately for the 3 fractions overburden and tailings, domestic-type commercial waste, and hazardous waste (table 3).

AC
•

Ytong <sup>®</sup> - AAC P2 0.40 and P4 0.50			
Indicator	P2 0.40	P4 0.50	
Overburden / tailings [kg/m <sup>3</sup> ]	315.4	367.30	
Domestic-type commercial waste [kg/m³]	2.78	2.78	
Hazardous waste [kg/m3]	0.45	0.51	

Overburden and tailings mainly occur due to coal and lignite extraction which are generally used for the production of the bonding agents (cement and chalk).

Impact The following figure shows the comparative contributions of raw materials, production, transport and packaging for 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC P2 0.40 and P4 0.50 for the impact categories Global Warming Potential (GWP), Ozone Depletion Potential (ODP), Acidification Potential (AP), Eutrophication Potential (EP), Photochemical Ozone Creation Potential (POCP).

In all environmental impacts, the highest contributions by far can be apportioned to the extraction and/or production of raw materials, at least 45% each. The second



Product group:	Autoclaved Aerated Concrete
Declaration holder:	Xella Baustoffe GmbH
Declaration number:	EPD-XEL-2009112-E

Issued 05-02-2009

highest, but with a significantly lower proportion in all impact categories, is the production of autoclaved aerated concrete (including electricity and thermal energy). Packaging and transportation of the raw materials are of secondary importance.





The absolute contributions of the production of 1 m<sup>3</sup> Ytong<sup>®</sup>-AAC P2 0.40 and P4 0.50 to the individual environmental impacts are shown in table 4:

Tabelle 4:	Absolute contributions of the production of Ytong <sup>®</sup> -AAC P2 0.40 and P4 0.50
	to the individual environmental impacts per cubic meter.

Ytong <sup>®</sup> - AAC P2 0.40 and P4 0.50			
Impact Category	Unit	P2 0.40	P4 0.40
Global Warming Potential	kg CO <sub>2</sub> -eqv.	178.7	217.1
Ozone Depletion Potential	kg R11-eqv.	9.99 * 10 <sup>-6</sup>	10.9 * 10 <sup>-6</sup>
Acidification Potential	kg SO <sub>2</sub> -eqv.	0.263	0.285
Eutrophication Potential	kg Phosphate-eqv.	0.044	0.049
Photochemical Ozone Creation Potential (POCP)	kg Ethene-eqv.	0.038	0.042

The production of the bonding agents cement and chalk make the largest contribution by far to all impact categories by far. Together, they contribute over 70% to the global warming potential and over 50% to the acidification potential for both gross density classes. With both gross density classes, the production contributes to the eutrophication potential in particular with approx. 25%. Electricity and thermal energy with at least 15% each have an influence on the individual impact categories which is by no means negligible. Additional materials or transport and packaging are of secondary importance.



Product group:Autoclaved Aerated ConcreteDeclaration holder:Xella Baustoffe GmbHDeclaration number:EPD-XEL-2009112-E

Issued 05-02-2009

#### 8 Evidence

A manufacturer declaration exists, according to which the composition of the basic materials, the production process and the product features of the Xella building components referred to, have not changed since the evidence named in the following was issued. The evidence is therefore completely valid.

RadioactivityMeasurement of nuclide concentration in Bq/kg for Ra-226, Th-232, K-40All mineral raw materials contain minor amounts of naturally radioactive substances.<br/>According to the measurements, the natural radioactivity enables an unrestricted use<br/>of this building material from the radiological point of view. /BfS 2008/

**Leaching** The leaching out of autoclaved aerated concrete is significant for the assessment of its post-use environmental impact once landfilled.

**Test point:** Prüfamt für bituminöse Baustoffe und Kunststoffe der Technischen Universität München (Testing Department for Bituminous Construction Materials and Synthetic Materials of the Technical University Munich).

**Result:** All criteria for the landfilling according to class 1 of the Technical Instructions on Waste from Human Settlements are fulfilled.

#### 9 PCR document and verification

This declaration is based on the Product Category Rules – Autoclaved Aerated Concrete

Review of the PCR-Documents by the Committee of Experts.	
Chairman of the Committee of Experts: Prof. DrIng. Hans-Wolf Reinhardt (University of Stuttgart, IWB)	
Independent verification of the declaration according to ISO 14025:	
internal external	
Validation of the declaration: Dr. Eva Schminke	

#### 10 References

- /GaBi 2003/ GaBi 4: Software und Datenbank zur Ganzheitlichen Bilanzierung. IKP, Universität Stuttgart und PE Europe GmbH, Leinfelden-Echterdingen, April 2003.
- /ISO 14040/ DIN EN ISO 14040: Umweltmanagement Ökobilanz Prinzipien und allgemeine Anforderungen, Deutsche Fassung EN ISO 14040:1997.
- /BfS 2008/Gehrke, K. Hoffmann, B., Schkade, U., Schmidt, V., Wichterey, K.: Natürliche<br/>Radioaktivität in Baumaterialien und die daraus resultierende Strahlenexposition -<br/>Zwischenbericht; Bundesamt für Strahlenschutz, Berlin 2008, 37 S.





Institut Bauen und Umwelt e.V. Publisher:

Institut Bauen und Umwelt e.V. Rheinufer 108 53639 Königswinter Tel.: 02223 296679-0 Fax: 02223 296679-1 Email: info@bau-umwelt.com Internet: www.bau-umwelt.com

AAC Forum Chairman: Dr. Hartmut Walther

Layout: PE International GmbH

Picture Credits: Xella Baustoffe GmbH

In the case of a doubt is the original EPD "EPD-XEL-2009112-D" applicable.