

Neutral mould-resistant silicone sealant for stone and marble



WHERE TO USE

Mapesil LM is a solvent-free sealant with a low modulus of elasticity specifically formulated for sealing materials sensitive to acids and plasticising agents, marble, granite, sandstone and quartz thanks to its chemical nature which deters surface bleeding or the migration of plasticising agents which would otherwise stain the substrate.

The chemical characteristics of the product also make it perfectly suitable for particularly delicate materials such as mirrors, bricks, cellular concrete and varnished or enamelled wood.

Mapesil LM generally forms an excellent bond on nonabsorbent substrates too, such as glass, ceramic, clinker, enamelled surfaces, water and solvent-based varnish, metals in general and on various types of plastic. It is also suitable for contact with absorbent mineral substrates such as concrete, render and fibre-cement.

This product generally forms a good bond on the above substrates even if a primer is not applied beforehand (contact the MAPEI Technical Services Department before).

Thanks to the low modulus of elasticity of **Mapesil LM**, it is suitable for sealing internal and external fillet and expansion joints, including those subject to high movements when in service, between:

- pre-fabricated panels;
- window/door fittings and wall surrounds;
- pipe-work and vertical walls;

• similar and/or different types of coating materials.

It is also suitable for sealing joints in floors with limited pedestrian traffic.

TECHNICAL CHARACTERISTICS

Mapesil LM is a one-component, solvent-free, neutral-reticulation silicone sealant which does not emit unpleasant odours, available in the form of a thixotropic paste. It is easy to apply on vertical and horizontal surfaces and reticulates at room temperature through the humidity present in the air to form a flexible sealant.

Seals made using **Mapesil LM** are extremely stable over time, even when exposed to inclement weather, industrial environments, temperature variations or water. The product remains flexible over a temperature range of between –40°C and +150°C.

Mapesil LM delays the formation of surface mould.

Mapesil LM generally offers good resistance to chemical agents. However, because of the wide range of products and service conditions, if in doubt carry out preliminary tests beforehand.

Mapesil LM bonds perfectly to most types of substrate used in the building industry without applying a primer beforehand (glass, ceramic, marble, aluminium, zincplated sheet metal, concrete, stainless steel and PVC).

Primer FD must be applied beforehand in the case of prolonged immersion in water.





Sealing an external stone dressing



Sealing an internal stone dressing

If in doubt, please contact the MAPEI Technical Services Department or carry out preliminary tests beforehand.

Mapesil LM is particularly suitable for surfaces sensitive to acids on which conventional neutral or acid sealants normally provoke changes in colour or staining of the substrate (e.g. stone, mirrors, etc.).

Mapesil LM complies with EN 15651-1 norm ("Sealants for internal and external façade elements") with performance rating F-EXT-INT-CC, with EN 15651-2 norm ("Sealants for glazing applications, intended for use in cold climates") type G-CC, with EN 15651-3 norm ("Sealants for joints in sanitary areas") type XS1 and EN 15651-4 norm ("Sealants for pedestrian walkaways") with performance rating PW-EXT-INT-CC.

RECOMMENDATIONS

Do not apply **Mapesil LM** on rubber, heavily-plasticised plastics or bitumen. The oil and plasticising agents in the substrate may migrate to the surface and compromise the bond or penetrate into the sealant leading to a variation in colour and mechanical characteristics.

- Do not use **Mapesil LM** if immersed constantly in chlorinated water.
- Do not use Mapesil LM for sealing floors subject to intense traffic (use Mapeflex PU45, Mapeflex PU20 or Mapeflex PU21).
- Do not use **Primer FD** when sealing stone or marble.

APPLICATION PROCEDURE

Surfaces to be sealed must be solid with no dust or loose parts and free of all traces of oil, grease, wax, old paintwork and rust.

In order to perform correctly, the sealant must be able to expand and contract freely once it has been applied in the joint.

It is important, therefore, that:

- it only bonds perfectly to the side walls of the joint and not to the bottom;
- the width of the joint is calculated correctly so that the product does not expand more than 25% of the initial width of the joint when in service;
- the thickness of seals using Mapesil LM is as indicated in the table to the side.

Also, to protect the substrate from staining, apply masking tape along the edges of the joint before extruding the **Mapesil LM**.

Regulate the depth of the joint to avoid **Mapesil LM** sticking to the bottom by inserting **Mapefoam** polystyrene foam cord in the joint.

Application of Primer FD

If a coat of **Primer FD** is required, apply the product with a small brush where required,

leave it to dry for a few minutes so that the solvent evaporates and then apply the **Mapesil LM**.

Application of Mapesil LM

Mapesil LM is available in 310 ml cartridges. Cut the tip of the cartridge near the thread and screw on the nozzle. Trim the tip of the nozzle at 45° according to the width of joint required and insert the cartridge into a suitable extrusion gun.

Finish the surface of the **Mapesil LM** with a suitable damp tool or a tool dipped in soapy water before the skin forms on the surface. For further information, please refer to the Safety Data Sheet available upon request.


Reticulation

When **Mapesil LM** is exposed to the air, the surrounding humidity sets off the reticulation reaction and the sealant becomes flexible.


The surrounding temperature only has a small impact on the reticulation rate of **Mapesil LM**, while the level of humidity in the surrounding air has the most influence. We highly recommend that the product is never applied if the temperature is below 0°C.

JOINT SIZE AND CONSUMPTION

EXPANSION JOINT



BUT JOINT



TECHNICAL DATA (typical values) Conforms to the following standards:	

- DIN 18545-2 class E
– DIN 18540
- ISO 11600-F class 25 LM
- ISO 11600-G class 25 LN
- ASTM C 920 class 25
- TT-S-00230 C class A
- TT-S-001543 A class A
- ASTM C 1248
- BS 5889 type A

PRODUCT IDENTITY		
Classification according to EN 15651-1:	F-EXT-INT-CC	
Classification according to EN 15651-2:	G-CC	
Classification according to EN 15651-3:	XS1	
Classification according to EN 15651-4:	PW-EXT-INT-CC	
Consistency:	thixotropic paste	
Colour:	white (100), grey (110), grey (111), grey (112), grey (113), anthracite (114), black (120), jasmine (130), beige (132) and transparent	
Density according to ISO 1183 Met. B (g/cm³):	1.02	
Dry solids content (%):	100	
EMICODE:	EC1 Plus - very low emission	
APPLICATION DATA (at +23°C - 50% R.H.)		
Application temperature range:	from +5°C to +40°C	
Extraction rate from a 3.5 mm nozzle at a pressure of 0.5 MPa (ml/min.):	50-70	
Time to form surface skin:	15 minutes	
Reticulation rate from outside to the inside (mm): - 1 day: - 7 days:	4 10	
FINAL PERFORMANCE		
Tensile strength according to ISO 8339 (N/mm²):	0.5	
Elongation at failure according to ISO 8339 (%):	250	
Tear resistance (ISO 34) (N/mm²):	4	
Shore A hardness (DIN 53505):	21	
Modulus of elongation according to ISO 8339 - Method A at 100% elongation (N/mm²):	0.35	
Maximum permitted movement in service (%):	25	
Resistance to water:	excellent	
Resistance to ageing:	excellent	
Resistance to atmospheric agents:	excellent	
Resistance to chemical agents, acids and diluted alkalis:	good	
Resistance to soap and detergents:	excellent	
Resistance to solvents:	limited	
Resistance to temperatures:	from -40°C to +150°C	










Sealing a façade joint with Mapesil LM



Cleaning

Traces of partially reticulated Mapesil LM may be removed from tools and the surface of the substrate with common solvents such as ethyl acetate, benzene or toluene. Once the product has completely reticulated, the silicone rubber may only be removed mechanically.

PACKAGING

Mapesil LM is available in 310 ml cartridges in white (100), grey (110), grey (111), grey (112), grey (113), anthracite (114), black (120), jasmine (130), beige (132) and transparent in display boxes containing 12 cartridges.

STORAGE

Mapesil LM cartridges may be stored for up to 18 months in a dry, cool area.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapesil LM is not considered as dangerous according to the European regulation redarding the classification of mixtures. It is however recommended to use gloves, eyes protection and to take the usual precaution taken when handling chemical products are recommended.

For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com



This symbol is used to identify Mapei products which give off a low level of volatile organic compounds (VOC) as certified by GEV (Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V.), an international organisation for controlling the level of emissions from products used for floors. from products used for floors.



Our Commitment To The Environment
MAPEI products assist Project Designers
and Contractors create innovative LEED
(The Leadership in Energy and Environmental
Design) certified projects, in
compliance with the U.S. Green
Publisher Commitment

Building Council.

All relevant references for the product are available upon request and from www.mapei.com

