

<p>Product composition</p>	<p>Characteristics</p> <p style="text-align: right;">7</p>	
<p>Float</p> <p>Resin interlayer</p>	<ul style="list-style-type: none"> ▶ Pyroguard EW60 is cuttable with specialist equipment ▶ Available in stock sheets 1580 x 2780 mm ▶ Internal and external installation (UV stable) ▶ Double sided fire resistance 	
<p>Technical characteristics</p>	<p>Physical features</p>	
<ul style="list-style-type: none"> ▶ Fire classification: EW60 ▶ Impact classification: 2B2 ▶ Light transmission: 85% ▶ Sound reduction: 35 dB ▶ U value: 5.1 W/m² K ▶ UV stability: yes 	<ul style="list-style-type: none"> ▶ Nominal Thickness: 11 mm ▶ Thickness tolerances: - 1 / + 1.4 mm ▶ Weight/m²: 26.7 kg ▶ Temperature range: - 20 / + 140 °C ▶ Min manufactured size: 	
	<p>Possible applications</p>	
<p>FLEXIBLE INDEPENDENT RESPONSIVE SPECIFIC TECHNICAL FIRST IN FIRE GLASS</p>	<p>Steel system</p> <p>Timber system</p> <p>Please see PV 07-V-249, page 93</p> <p>CF 257 p 34</p>	
<p>34</p> <p>06/2015</p>		

The diagrams in this document are for guidance purpose only, for actual projects specific drawings are required.